

CastoDur Diamond Plates®

# CDP® 1001



CDP® 1001 – another step forward

- Unique combination of ultra-hard phases providing best service life, even in most demanding applications
- Larger surface area of wearfacing
- Readily weldable base plate for fast installation
- Easy to form by bending and rolling



WEAR PLATES



**CDP® are engineered for exceptional wear resistance.**

This performance results from:

1. Ultra-hard phases anchored in a tough matrix. Their hardness is typically 2-3 times higher than the most abrasive media used in industrial processes.
2. The Unique geometry of the hard phases dispersed between regular needle shaped phases which are all firmly anchored within a tough matrix.

This prevents premature “washing out” of the hard phases from the “softer” matrix by wear mechanisms.

The unique process of cooling control gives extremely low levels of dilution for this type of wearplate. Consequently, a very reliable and constant wear rate is guaranteed throughout the entire thickness of the protective coating.

**CDP® 1001**

CDP® 1001 is the latest addition to our family of highest performance wearplates. Unique weld bead geometry provides additional value, improving even more wear performance and minimizing plate scrap. Coating technology preserves all mechanical values of base material allowing further processing by rolling and bending.



**Weardfaced area dimensions:** 1400x2930 mm  
**Base material:** S235 JR+N – others available on request  
**Macro hardness:** 58 – 60 HRC, hard phases (carbides) 1500 – 2200 HV  
**Max. service temperature:** 350°C

**Available thicknesses:**

Designation	ESC code	Base material [mm]	Wearfacing [mm]
CDP® 1001 DP 0604	762695	6	4
CDP® 1001 DP 0804	762267	8	4
CDP® 1001 DP 0805	762268	8	5
CDP® 1001 DP 1005	762269	10	5
CDP® 1001 DP 1505	762270	15	5

**Eurocode:** 8395

## Your resource for protection, repair and joining solutions

**Statement of Liability:** Due to variations inherent in specific applications, the technical information contained herein, including any information as to suggested product applications or results, is presented without representation or warranty, expressed or implied. Without limitation, there are no warranties of merchantability or of fitness for a particular purpose. Each process and application must be fully evaluated by the user in all respects, including suitability, compliance with applicable law and non-infringement of the rights of others, and Messer Eutectic Castolin and its affiliates shall have no liability in respect thereof.