



Surfacing Polymer

MeCaFix 130

Ceramic Rebuild Compound and Tile Adhesive

TECHNICAL DATA SHEET



DESCRIPTION

MeCaFix 130 is a fine ceramic filled trowelable repair compound for resurfacing and protecting worn processing equipment exposed to corrosion, cavitation, and alkaline/acidic chemicals. MeCaFix 130 allows the protection of working surfaces in all positions without sag. This ceramic coating is extremely versatile and can be used as a standalone coating material or as an all in one adhesive and grout for the installation of alumina ceramic tile.

APPLICATIONS

- Cracked Casings
- Pump Housings
- Resurfacing Metal Loss
- Chutes
- Tube Sheet Repair
- Ceramic Tile Adhesive/Grout
- Butterfly Gate Valve Repairs
- Hoppers

COVERAGE DATA

Theoretical coverage rate data

Practical Coverage = Theoretical Coverage - Waste Factor

Kit Weight	Recommended Coating Thickness	Theoretical Coverage Rate
3.3 lb (1.5 Kg)	125 mils (3.2 mm)	2.57 ft ² (0.24 m ²)
32 lb (14.5 kg)	125 mils (3.2 mm)	24.85 ft ² (2.3 m ²)

PACKAGING

0.8 liter / 0.2 Gal. / 1.5 Kg / 3.3 lb Kit
7.2 liter / 1.9 Gal. / 14.5 Kg / 32 lb Kit

TECHNICAL DATA

Performance / Property		Results
Hardness	ASTM D2240	[Shore D] 86
Pull Off Adhesion	ASTM D4541	≥ 4,100 psi (≥ 28 MPa)
X Cut Adhesion	ASTM D6677	Rating 10
Taber Abrasion	ASTM D4060	65 mg loss
Atlas Cell, 194°F (90°C)/7 days NACE 0174		Pass

PHYSICAL DATA

Color	Blue
Mix Ratio	3:1 by volume
Mix Ratio	6:1 by weight
Sag Resistance (250 mils / 6.3 mm)	No Sag
Working Life (77°F / 25°C)	25 minutes
Low Temperature Application	50°F (10°C)
Max. Re-coat Window (77°F / 25°C)	8 hours
Percent Solids	100%
Odor	Slight to nil
Mixed Viscosity	Paste
Mixed Density	1.97 g/ml
Max. Operating Temp. - Wet Service	176°F (80°C)
Max. Operating Temp. - Dry Service	302°F (150°C)
Cure Time - Touch (77°F / 25°C)	4 hour
Cure Time - Handle (77°F / 25°C)	10 hours

Before applying this product, please refer to the Application Instructions.

YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



EUTECTIC CORPORATION
N94 W14355 Garwin Mace Drive
Menomonee Falls, WI 53051 USA
Tel.: +1 (800) 558-8524

EUTECTIC CANADA
428, rue Aimé-Vincent
Vaudreuil-Dorion, Québec
J7V 5V5 Canada
Tel.: +1 (800) 361-9439



mecatecpolymers.com