

A Nickel Based Blended Powder for the Plasma Transferred Arc (PTA) Process

EuTroLoy® 16360G



COATING

- Best for crack resistance
- Outstanding abrasion and erosion resistance
- Superior resistance to galling and fatigue
- Uniform powder size distribution for trouble free operation
- Excellent welding characteristics
- Available in 3 different carbide types



DESCRIPTION:

EuTroLoy 16360G is a gas atomized nickel based alloy that is blended with 60% (by weight) of tungsten carbide (WC) to form a composite alloy.

EuTroLoy 16360G is available in 3 different carbide types;

1. 16360G-CWC: 60% Cast Tungsten Carbide
2. 16360G-MWC: 60% Macrocrystalline Tungsten Carbide
3. 16360G-SWC: 60% Spherical Tungsten Carbide

The low hardness matrix is designed to withstand impact and fatigue while the WC offers superior abrasion and erosion resistance.

The coatings produced are hard, dense and especially resistant to low stress abrasion and erosion. Careful control of the chemistry and particle size distribution of both powder components assures consistent and reliable performance in standard PTA welding equipment and in the most challenging applications.

COATING PROPERTIES:

Typical Matrix Hardness: 30-35 HRC

Typical Carbide Hardness (VHN300):

CWC: 2200
MWC: 2100
SWC: 3000

Available Carbide Types:

CWC: W2C-WC (angular)
MWC: WC (angular)
SWC: W2C-WC (spherical)

Nomical Composition: WC, Carbon, Chromium, Silicon, Boron, Iron, Nickel

PROCEDURE FOR USE:

Remove damaged material. Clean areas to be welded. Match heat input during welding to component dimensions. Follow the prepared welding procedure for the specific base metal chemistry. Keep dilution with base metal low. Allow workpiece to slowly cool upon completion of welding.

It is important that amperage and voltage be kept as low as possible to maintain WC integrity, while maintaining a well bonded overlay.

FINISHING:

Coatings of EuTroLoy 16360G can be finished by grinding.

TYPICAL APPLICATIONS:

The overlay offers excellent resistance to abrasion, erosion, corrosion, fatigue, heat scale, galling, scoring and seizing on carbon steels, stainless steels, cast iron and nickel alloys.

16360G-CWC: Most commonly used WC on the market for severe wear from abrasion and/or erosion. Generally used for low stress abrasion in Mining and Mineral Processing environments. Due to its eutectic structure, it is recommended that low welding currents are used to minimize carbide dissolution.

16360G-MWC: A single crystal WC that withstands the intense heat of arc welding better than CWC. Wear performance and applications are similar to CWC.

16360G-SWC: Primarily used where high stress (2-body) abrasion is encountered. Applications include crushing equipment, track undercarriage, drill systems.

HEALTH & SAFETY:

To ensure a safe work environment observe normal welding practices, provide appropriate eye, hearing, skin and respiratory protection and pay attention to air flow patterns. For general weld practices, refer to ANSI Z49.1:2012 - "Safety in Welding, Cutting, and Allied Processes". Welding is a completely safe process when performed in accordance with proper safety measures. Become familiar with local safety regulations before starting operations. DO NOT operate your equipment or use the material supplied, before you have thoroughly read the equipment instruction manual. Contact Eutectic for Material Safety Data Sheet (MSDS) information. DISREGARDING THESE INSTRUCTIONS MAY BE HAZARDOUS TO YOUR HEALTH.

YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



Eutectic Canada
Eastern Canada
428, rue Aime Vincent
Vaudreuil-Dorion, Quebec
Phone: (800) 361-9439
Fax: (514) 695-8793

Eutectic Canada
Western Canada
7722 - 69 Street
Edmonton, Alberta
Phone: (800) 661-3620
Fax: (780) 465 8076

www.eutectic.ca

Statement of Liability: Due to variations inherent in specific applications, the technical information contained herein, including any information as to suggested product applications or results, is presented without representation or warranty, expressed or implied. Without limitation, there are no warranties of merchantability or of fitness for a particular purpose. Each process and application must be fully evaluated by the user in all respects, including suitability, compliance with applicable law and non-infringement of the rights of others, and Eutectic Corporation and its affiliates shall have no liability in respect thereof.

16360G Feb-15 © 2008, Eutectic Canada Inc., ® Reg. T.M., Printed in Canada