

Superior all position, controlled-hydrogen electrode for welding structural steel when impact properties are called for

EutecTrode® 7018-1



WELDING

- Excellent for steels and joints subject to stress and strain
- Provides exceptional impact toughness at low service temperatures
- Runs smooth in all positions with excellent vertical-up capabilities
- High quality, flexible flux coating with less break-off or chipping, even when bent or mishandled
- Moisture resistant coating, excellent slag removal
- CERTIFICATIONS:

AWS A5.1-91:E7018-1

ASME SFA 5.1: E7018-1

CWB: CSA W48



DESCRIPTION:

EutecTrode 7018-1 is a high strength ferritic electrode. This high quality, all position, low hydrogen electrode features rapid deposition.

Deposits have good ductility, are dense, crack-free, and of X-ray quality. EutecTrode 7018-1 is excellent for steels sensitive to cracking when welded with conventional mild steel electrodes.

Conforms to:

AWS A5.1-91: E7018-1; ASME SFA 5.1: E7018-1; CWB: CSA W48

TECHNICAL DATA:

Tensile Strength:	80,000 psi (550 MPa)
Yield Strength:	71,000 psi (489 MPa)
Charpy V-Notch:	up to 70 ft-lb at -45°C (-50°F)
Polarity:	AC/DC (+)

WELDING PARAMETERS:

Preparation: Clean weld area of scale and/or oxide. A nominal preheat of 65°C (150°F) is advised if part is below 5°C (40°F) or over 25 mm (1") thick. For higher carbon steels, higher preheats will be needed. Do not preheat manganese steel castings above 205°C (400°F) as this will cause time-temperature embrittlement.

Technique: Maintain the optimum electrode stickout and hold a 75° angle from the vertical in the direction of travel. Do not weave excessively. Wide beads can cause porosity, excessive base metal overheating, and degrade the weld deposit wear properties. Back whip craters to reduce cracking tendencies and potential out-gassing.

Post-welding: Allow parts to slow cool in still air. High carbon steels and air hardenable steels should be covered with a heat-retardant blanket or by other means. If steel composition is unknown, slow cool at a rate of 38°C (100°F) per hour.

TYPICAL APPLICATIONS:

For "tramp" and "problem" steels high in sulphur, phosphorus, or other elements added to improve the machinability of the steel.

For fabrication of "H" and "I" beams, angle and channel iron, pipelines, and all other steel structures. For circular tube to plate welds, and other type joints subject to stress and strain. Excellent for applications where low temperature charpy V-notch impacts are required.

WELDING PARAMETERS - AC/DC (+)	
Diam.	Amperage
2.4 mm (3/32")	60-100
3.2 mm (1/8")	110-150
4.0 mm (5/32")	140-220
4.8 mm (3/16")	220-280

YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



Eutectic Corporation
N94 W14355 Garwin Mace Drive
Menomonee Falls, WI 53051 USA
P 800-558-8524 • F 262-255-5542
www.eutectic.com

Eutectic Canada
428, rue Aime Vincent
Vaudreuil-Dorion, Quebec J7V 5V5
Phone: (800) 361-9439
Fax: (514) 695-8793
www.eutectic.ca

Statement of Liability: Due to variations inherent in specific applications, the technical information contained herein, including any information as to suggested product applications or results, is presented without representation or warranty, expressed or implied. Without limitation, there are no warranties of merchantability or of fitness for a particular purpose. Each process and application must be fully evaluated by the user in all respects, including suitability, compliance with applicable law and non-infringement of the rights of others, and Eutectic Corporation and its affiliates shall have no liability in respect thereof.

7018-1- Feb 2018© 2008, Eutectic Corporation, © Reg. T.M., Printed in Canada.

Part of the Messer World ■■