

CastoDur® Diamond Plates

Tough Chrome Carbide Overlay for Severe Abrasion and Moderate Impact

Rough & Ready® Sizeable Wear Strips



WEAR PLATES


- Special alternating weld-overlay pattern
- Strips are easily cut, formed and installed
- Conveniently packed 3 strips to a box



DESCRIPTION:

The special alternating weld-overlay pattern of Eutectic's Rough & Ready Sizeable Wear Strips provides both superior wear protection along with easy cutting and forming.

Convenient 3" (7.62cm) x 48" (121.92cm) Rough & Ready Sizeable Wear Strips can be cut with an ordinary cutting torch or sheared to the desired length. They can also be formed to a curved surface simply by using moderate heat and pressure. The strips are easily attached by welding into place with Eutectic welding products. For custom size Wear Strips please contact Eutectic's Technical Service Department.



Typical excavator bucket application

PRODUCT INFORMATION:

Part Number:	8010348
Strip Size:	3" (7.62cm) x 48" (122 cm)
Packaging:	Three strips per box

OVERLAY PROPERTIES:

Nominal Hardness: HRC 55-59
Microhardness: DPH 1800-2000
Macrohardness: HRC 55-59
Max Service Temperature: 1100° F (approx. 593°C)
Overall Wear Plate Density: 0.284 lb/in³
ASTM G65 Wear Test Results: 23-mm³
Typical Analysis with Principal Elements: Fe-Cr-C

TYPICAL APPLICATIONS AND INDUSTRIES:

APPLICATIONS:

- Bucket Skid Pads
- Backhoe Buckets
- Excavator Buckets
- Edge Runners
- Front End Loader Buckets

INDUSTRIES:

- Construction
- Mining
- Agriculture
- Quarrying
- Earth Moving

YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



EUTECTIC CORPORATION
N94 W14355 Garwin Mace Drive
Menomonee Falls, WI 53051 USA
Tel.: +1 (800) 558-8524
eutectic.com

EUTECTIC CANADA
428, rue Aimé-Vincent
Vaudreuil-Dorion, Québec
J7V 5V5 Canada
Tel.: +1 (800) 361-9439
eutectic.ca



Statement of Liability: Due to variations inherent in specific applications, the technical information contained herein, including any information as to suggested product applications or results, is presented without representation or warranty, expressed or implied. Without limitation, there are no warranties of merchantability or of fitness for a particular purpose. Each process and application must be fully evaluated by the user in all respects, including suitability, compliance with applicable law and non-infringement of the rights of others, and Eutectic Corporation and its affiliates shall have no liability in respect thereof.

R&R 03/16 © 2008, Eutectic Corporation, ® Reg. T.M., Printed in the U.S.A.