Gas Shielded, Peripheric Continuous Electrode for Semi-Automatic and Automatic Robotic Welding

EnDOtec DO*48



- Severe abrasion and erosion resistant graded tungsten carbide alloy
- Ferrous matrix reinforced with dispersed, tenacious recrystallised phases
- Full properties with single pass
- Deposits very resistant to grinding



DESCRIPTION:

EnDOtec DO*48 is an exclusive, gas shielded, metal cored alloy wire ideal for maintenance and repair applications or batch manufacturing where the highest integrity welding, efficiency and productivity are required.

The slag-free deposit features a high density of Cast Tungsten Carbide particles evenly distributed in a ironbased matrix. This gives exceptional resistance to abrasive and erosive particles with moderate impact.

TECHNICAL DATA:

Typical Matrix Hardness: 55 HRC Micro Hardness of Carbide: 2200 HV

Machinability: Grind Only Shielding Gas: 98% Ar / 2%O₂ Diameter of Wire: 1/16" (1.6mm)

Polarity: DCEP(+)
Weight: 30 Lb Spool

PROCEDURE FOR USE:

Remove old welding deposits and worn metal with ChamferTrode. Degrease and remove all contaminant's. Pre-heating temperatures are determined by base metal. Push or pull the electrode at an angle of 70-80° to ensure optimal fusion. If required, a second pass should only be deposited while the weld is still hot.

TYPICAL APPLICATIONS

For semi-automatic and robotic welding applications. Protective coating of parts particularly in the following industries...

Mining, Quarries, Drilling, Tunneling, Public Works

Used for...

- Extrusion press parts
- Transport screws
- Conveyors
- Pump rotors and bodies
- Cylinder crushers
- · Mixer paddles

TYPICAL WELDING PARAMETERS

1/16" (1.6MM)	TRANSFER	VOLTAGE	AMPERAGE	STICK-OUT	GAS FLOW
Typical	Short-Arc	18 - 22	140 MAX	3/4" - 1 1/4"	25-35 SCFH
Optimum	Short-Arc	20	110-120	1"	30 SCFH

YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



EUTECTIC CORPORATION N94 W14355 Garwin Mace Drive Menomonee Falls, WI 53051 USA Tel.: +1 (800) 558-8524 eutectic.com EUTECTIC CANADA 428, rue Aimé-Vincent Vaudreuil-Dorion, Québec J7V 5V5 Canada Tel.: +1 (800) 361-9439 eutectic.ca

