

General Purpose Hardfacing Electrode for Abrasion and Impact

# EutecTrode® 5002



## WELDING

- Easy and complete slag removal
- Crack-resistant deposits
- Excellent for field repairs
- Welder-friendly



## DESCRIPTION:

EutecTrode 5002 is a general purpose hardfacing electrode for resistance to abrasion and impact. It is suitable for the surfacing of new or worn machine components used for earthmoving or rock crushing.

## TECHNICAL DATA:

Typical Hardness (single pass): 54-58 HRC  
Polarity: AC/DC (+)  
Positions: Flat and Horizontal

### Recommended Amperages

|      |              |               |               |
|------|--------------|---------------|---------------|
| Dia  | 1/8" (3.2mm) | 5/32" (4.0mm) | 3/16" (5.0mm) |
| Amps | 100-140      | 140-180       | 180-230       |

## TYPICAL APPLICATIONS:

### APPLICATIONS

Shredders  
Feed Screws  
Bucket Teeth  
Crushers

### INDUSTRIES

Recycling  
Pulp and Paper  
Mining  
Quarry

## WELDING PARAMETERS:

**Preparation:** Clean the weld area and remove scale and oxide. For parts below 40°F or over 1" thick, preheat to 150°F. Higher carbon steels require higher preheat (300°F - 500°F). Do not preheat Hadfield manganese steel castings above 200°F.

**Technique:** Maintain a medium to short arc. The electrode should be inclined at a 15-30° angle in the direction of travel. Weld using stringer beads or 2x weaving. Be advised that weaving more than 2x the electrode diameter is not advised as it may overheat the base metal and degrade weld deposit wear properties. Prior to extinguishing the arc, back whip the craters to reduce crater cracking.

**Post-welding:** Slow cool parts in still air. High carbon steels and air hardenable steels should be covered with a heat retardant blanket.

## YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



**EUTECTIC CORPORATION**  
N94 W14355 Garwin Mace Drive  
Menomonee Falls, WI 53051 USA  
Tel.: +1 (800) 558-8524  
eutectic.com

**EUTECTIC CANADA**  
428, rue Aimé-Vincent  
Vaudreuil-Dorion, Québec  
J7V 5V5 Canada  
Tel.: +1 (800) 361-9439  
eutectic.ca



Statement of Liability: Due to variations inherent in specific applications, the technical information contained herein, including any information as to suggested product applications or results, is presented without representation or warranty, expressed or implied. Without limitation, there are no warranties of merchantability or of fitness for a particular purpose. Each process and application must be fully evaluated by the user in all respects, including suitability, compliance with applicable law and non-infringement of the rights of others, and Eutectic Corporation and its affiliates shall have no liability in respect thereof.

5002 07/2017 © 2008, Eutectic Corporation, © Reg. T.M., Printed in the U.S.A.