



An Atomized, Tin-Based  
Alloy Powder

# **BabTec**

# **29240**



- Designed for use with thermal spray equipment using the LT Accessory Air Shroud Package
- The tin alloy is similar to SAE 23 type II Babbitt
- Used for rebuilding most common tin-based Babbitt bearings
- Not recommended for bearings containing significant amounts of lead

# BabTec 29240

29240 is an atomized tin-based alloy powder suitable for coating applications using combustion thermal spray equipment such as the TeroDyn® 2000 or TeroDyn 3000 systems when equipped with the specially designed low temperature LT Accessory Air Shroud Package. The tin alloy is similar to SAE 23 type II Babbitt. It can be used for rebuilding most common tin-based babbitt bearings. It is not recommended for those containing significant amounts of lead.

## TECHNICAL DATA

| Typical Powder Properties    |   |
|------------------------------|---|
| Nominal Composition:         | Tin, Copper, Antimony, Lead                                   |
| Hall Flow Rate:              | 17 seconds  |
| Bulk Density:                | 4.0 g/cc  |
| Powder Coverage:             | 0.06 lbs/ft <sup>2</sup> @ 0.001"                             |
| Typical Coating Properties   |   |
| Hardness:                    | Rockwell Y Scale 30   |
| Bond Strength (ASTM C633):   | Tinned with 157 PA: 7,000 psi<br>Bond coat - Ni/Al: 2,000 psi |
| Maximum Service Temperature: | 250°F (121°C)   |
| Density:                     | 6.67 g/cc   |
| Melting Point:               | 466°F (241°C)   |
| Thickness Limitation:        | None  |

## PROCEDURE FOR USE

### Recommended Parameters

#### TD 2000 (Oxy-Acetylene)

|                  |                              |
|------------------|------------------------------|
| Nozzle:          | LT 250                       |
| LT Air Shroud:   | 30 psi                       |
| Module Adaptor:  | Red/Yellow                   |
| Oxygen:          | 50 psi / 28 flow             |
| Fuel Gas:        | Acetylene @ 12 psi / 32 flow |
| T-Valve Setting: | 13 clicks                    |
| Coating Rate:    | 20 lb/hr                     |
| Spray Distance:  | 4 to 6 inches                |

#### TD 2000 (Oxy-Propylene)

|                  |                               |
|------------------|-------------------------------|
| Nozzle:          | LT 260P                       |
| LT Air Shroud:   | 30 psi                        |
| Module Adaptor:  | Red/Yellow                    |
| Oxygen:          | 80 psi / 24 flow              |
| Fuel Gas:        | Propylene* @ 30 psi / 24 flow |
| T-Valve Setting: | 10 clicks                     |
| Coating Rate:    | 20 lb/hr                      |
| Spray Distance:  | 5 to 6 inches                 |

\*Use Linde grade FG-2 or equivalent

#### TD 3000

|                |                             |
|----------------|-----------------------------|
| Nozzle:        | LT 250                      |
| LT Air Shroud: | 40 psi                      |
| Acetylene:     | 12 psi / 32 flow            |
| Oxygen:        | 50 psi / 32 flow            |
| Carrier Gas:   | (Ni or Ar) 55 psi / 40 flow |
| Terometer**:   | 100                         |
| Spray Rate:    | 40 lb/hr                    |
| Air Vibrator:  | 20 psi                      |

\*\*Use slotted pick-up tube and 12 foot black powder feed hose

## TYPICAL APPLICATIONS

- Heavy-duty bearings
- Split bearings
- Turbine bearings
- Drive-shaft bearings
- High-speed bearings

Observe normal spraying practices, respiratory protection and proper air flow pattern advised. For general spray practices, see AWS Publications AWS C2. 1-73, "Recommended Safe Practices for Thermal Spraying and AWS T55-85, "Thermal Spraying, Practice, Theory and Application." Thermal spraying is a completely safe process when performed in accordance with proper safety measures. Become familiar with local safety regulations before starting spray operations. DO NOT operate your spraying equipment or use the spray material supplied, before you have thoroughly read the equipment instruction manual. Refer to the Eutectic website for Material Safety Data Sheet (MSDS) information. DISREGARDING THESE INSTRUCTIONS MAY BE HAZARDOUS TO YOUR HEALTH.



**Eutectic Corporation:**  
N94 W14355 Garwin Mace Dr.  
Menomonee Falls WI, 53051 USA  
+1 800. 558. 8524 • eutectic.com

**Eutectic Canada:**  
428, rue Aimé-Vincent Vaudreuil-Dorion,  
Québec J7V 5V5 Canada  
+1 800. 361. 9439 • eutectic.ca



Follow Us On...

