




Nickel-Base Alloy Powder
for the Plasma Transferred Arc
Welding (PTAW) Process

EuTroLoy[®] **16801**



- Specially developed for the plasma transferred arc welding process
- Outstanding corrosion resistance
- Low coefficient of friction

EuTroLoy 16801

EuTroLoy 16801 is a nickel base alloy designed for the plasma transferred arc welding (PTAW) process providing hard, dense coatings. The alloy provides resistance to general corrosion, pitting, crevice corrosion, intergranular attack, and stress corrosion cracking.

TECHNICAL DATA

Typical Values	
Hardness:	20 HRC
Density:	8.69 g/cm ³
Nominal Particle Size:	80 x 270 US Mesh (-180 / +53 µm)
Max. Service Temperature:	1250°F (675°C)

Nominal Composition:

Ni, Cr, Mo, W, Fe

PROCEDURE FOR USE:

All surfaces to be coated should be thoroughly cleaned, removing all contaminants, oxides and grease.

EuTroLoy 16801 powder is made for use in Eutectic's GAP PTA equipment. Please contact Eutectic Technical Services to determine which GAP equipment is right for your coating needs.

TYPICAL APPLICATIONS

EuTroLoy 16801 can be used for many applications such as marine, power, chemical processing, pollution control, paper processing, and waste disposal industries.

To ensure a safe work environment observe normal welding practices, provide appropriate eye, hearing, skin and respiratory protection and pay attention to air flow patterns. For general weld practices, refer to ANSI Z49.1:2012 - "Safety in Welding, Cutting, and Allied Processes". Welding is a completely safe process when performed in accordance with proper safety measures. Become familiar with local safety regulations before starting operations. DO NOT operate your equipment or use the material supplied, before you have thoroughly read the equipment instruction manual. Contact Eutectic for Material Safety Data Sheet (MSDS) information. DISREGARDING THESE INSTRUCTIONS MAY BE HAZARDOUS TO YOUR HEALTH.



Eutectic Corporation:
N94 W14355 Garwin Mace Dr.
Menomonee Falls WI, 53051 USA
+1 800. 558. 8524 • eutectic.com

Eutectic Canada:
428, rue Aimé-Vincent Vaudreuil-Dorion,
Québec J7V 5V5 Canada
+1 800. 361. 9439 • eutectic.ca



Follow Us On...

