



An Aluminium - Bronze Wire
Made Exclusively for the
Twin Wire Arc Spray Process

EuTronic[®] Arc 552 Wire



- High bond strength
- Self-bonding to most metals including copper-base alloys
- Good abrasion and corrosion resistance
- Widely used for machine element repair

EuTronic® Arc 552AS

EuTronic Arc 552 is an aluminum-bronze wire designed specifically for the Twin Wire Arc process. The coatings produced are characterized by high bond strength and are considered self-bonding to most metals including copperbase alloys.

EuTronic Arc 552 will produce extremely dense coatings which exhibit good, general resistance to abrasion and corrosion. In addition, the coatings produced are readily machined to a 30-35 micro inch finish with standard high speed steel tooling.

EuTronic Arc 552 coatings are widely used for machine element repair applications.

TECHNICAL DATA

Typical Values	
Typical Hardness:	67 HRB
Bond Strength:	7000 psi
Deposit Rate:	9 lb/hr/100 amps
Deposit Efficiency:	75%
Wire Coverage:	0.9 oz/ ft ² /0.001 in. thick
Coating Density:	6.3 g/cc
Melting Point:	1800°F (982°C)

PROCEDURE FOR USE:

Surface should be clean, white metal, with no oxides (rust), dirt, grease, or oil on the surface to be coated.

Note: It is best not to handle surfaces after cleaning.

Recommended method of preparation is to grit blast with 24 mesh aluminium oxide.

Please contact your Eutectic Surface Coatings Specialist for more information.

Spray Parameters:

Diameter: 1.6 mm
Air Pressure: *50 – 60 psi
Voltage: *20-21
Amperage: *100-200
Standoff: *4-8 in.

**Parameters are typical and may vary depending on the equipment used. Contact your equipment manufacturer for optimum spray parameters.*

TYPICAL APPLICATIONS

- Bond Coating
- Rebuild Worn Bearing Areas
- Pump Shafts and Housings
- Air Seals
- Rebuild Propeller Shafts (Aluminum Bronze Components)

To ensure a safe work environment observe normal welding practices, provide appropriate eye, hearing, skin and respiratory protection and pay attention to air flow patterns. For general spray practices, see AWS Publications AWS C2. 1-73, "Recommended Safe Practices for Thermal Spraying" and AWS T55-85, "Thermal Spraying, Practice, Theory and Application." Thermal spraying is a completely safe process when performed in accordance with proper safety measures. Become familiar with local safety regulations before starting spray operations. DO NOT operate your spraying equipment or use the spray material supplied, before you have thoroughly read the equipment instruction manual. Refer to the Eutectic web site for Material Safety Data Sheet (MSDS) information. . DISREGARDING THESE INSTRUCTIONS MAY BE HAZARDOUS TO YOUR HEALTH.



Eutectic Corporation:
N94 W14355 Garwin Mace Dr.
Menomonee Falls WI, 53051 USA
+1 800. 558. 8524 • eutectic.com

Eutectic Canada:
428, rue Aimé-Vincent Vaudreuil-Dorion,
Québec J7V 5V5 Canada
+1 800. 361. 9439 • eutectic.ca



Follow Us On...



03-2021