

Flux Coated Cadmium-Free Silver Brazing Rod

EutecRod® 1030 FC

- Useful for parts with no uniform clearance
- Extremely flexible flux coating for difficult to reach applications
- Low zinc content minimizes problems due to excessive heating
- No preparatory fluxing necessary
- Recommended for brazing stainless steel, nickel or nickel alloys where stress cracking occurs during the heating process
- Suitable for brazing thin sections or thin cracks
- Good corrosion resistance

EutecRod[®] 1030 FC

A white colored, flux coated, brazing rod. Available in 18" lengths in 1/16" and 3/32" diameters. Packaged in 1 lb. and 5.5 lb. packs.

TECHNICAL DATA

Typical Values	
Solidus:	1145°F (618°C)
Liquidus:	1205°F (651°C)
Brazing Range:	1205 - 1400°F (651 - 760°C)
Specific Gravity:	9.49
Density:	4.986 oz/cu. in.
Electrical Conductivity:	11.9% IACS
Electrical Resistivity:	14.5 Michrohm-cm
For Joint Clearances:	.001 to .005 inches
Max. Operating Temp.:	400°F (204°C) continuous service 600°F (315°C) intermittent service

PROCEDURE FOR USE

PREPARATION: The base metal surfaces to be brazed must be clean and free of all dirt, oil, grease and oxides such as rust.

FINISHING: All the corrosive flux residue must be removed after brazing. Rinse with water while the parts are still warm, or rinse with hot water.

AVAILABILITY: Available in 18" lengths in 3/64", 1/16" and 3/32" diameters. Packaged in 0.5 lb., 1 lb., 2 lb. and 5.5 lb. packs.

TYPICAL APPLICATIONS

Suitable for brazing thin sections of fabricated steel boxes, butt joints, fixtures, brass wave guides, brass/ copper radiator repair, heat exchangers (thin cracks) and valves.



Eutectic Corporation: N94 W14355 Garwin Mace Dr. Menomonee Falls WI, 53051 USA +1 800. 558. 8524 • eutectic.com Eutectic Canada: 428, rue Aimé-Vincent Vaudreuil-Dorion, Québec J7V 5V5 Canada +1 800. 361. 9439 • eutectic.ca



