



MeCaPrime 10

TECHNICAL DATA SHEET

Concrete penetrating sealer and primer

DESCRIPTION

MecaPrime 10 is a low viscosity, micronized fiber reinforced sealer and primer designed to impart excellent adhesion to cold and damp concrete. MeCaPrime 10 offers very good chemical resistance and is suitable as a base layer for chemical immersion service. MeCaPrime 10 incorporates optical fluorescing pigment that provides visual inspection to ensure proper film coverage and improves pinhole detection of the primary topcoat. The surface finish resists amine blushing even when cured at cold temperature or high humidity. Suitable as a primer for MeCaCorr chemical resistant linings.

APPLICATIONS

Concrete primerSteel primerBonding adhesive

COVERAGE DATA

Theoretical coverage rate data 150 microns = 14.86 square meter/kit 6 mils = 160 square feet/kit

Practical coverage rate data Practical coverage = Theoretical coverage X (1 - % waste factor)

COATING DRY FILM THICKNESS

Suggested thickness - 100 to 175 microns (4 to 7 mils)

PACKAGING

2.5kg / 0.6 gallon

TECHNICAL DATA

Performance / Property		Results
Hardness	ASTM D 2240	[Shore D] 80
Pull Off Adhesion	ASTM D 4541	≥ 4,900 psi (≥34 MPa)
Pull Off Adhesion	(concrete)	400 psi (≥2.7 MPa)
X Cut Adhesion	ASTM D 6677	Rating 10
Tensile Strength	ASTM D 638	8,590 psi
Compressive Strength	ASTM D 695	13,000 psi
Flexibility	ASTM D 522	3" mandrel
Flexural Strength	ASTM D 790	≥ 13,488 psi
Elongation		5%

PHYSICAL DATA

Color	Amber clear
Mix Ratio	1.72:1 by volume
	2:1 by weight
Pot Life (77°F / 25°C)	38 minutes
Low Temperature Application	50°F (10°C)
Max. Re-coat Window (77°F / 25°C)	48 hours
Solvent Content	Zero
Odor	Low
Mixed Viscosity	2,200 mPa-s (cP)
Mixed Density	1.10 g/ml
Max. Operating Temp Wet Service	120°F (50°C)
Max. Operating Temp Dry Service	195°F (90°C)
Cure Time - Touch (77°F / 25°C)	6 hours
Cure Time - Handle (77°F / 25°C)	10 hours

Before applying this product, please refer to the Application Instructions.



YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



EUTECTIC CORPORATION N94 W14355 Garwin Mace Drive Menomonee Falls, WI 53051 USA Tel.: +1 (800) 558-8524 eutectic.com EUTECTIC CANADA 428, rue Aimé-Vincent Vaudreuil-Dorion, Québec J7V 5V5 Canada Tel.: +1 (800) 361-9439 eutectic.ca



mecatecpolymers.com

Statement of Liability: Due to variations inherent in specific applications, the technical information contained herein, including any information as to suggested product applications or results, is presented without representation or warranty, expressed or implied. Without limitation, there are no warranties of merchantability or of fitness for a particular purpose. Each process and application must be fully evaluated by the user in all respects, including suitability, compliance with applicable law and non-infringement of the rights of others, and Eutectic Corporation and its affiliates shall have no liability in respect thereof.