

# MeCaWear A5

Wear Protection Compound with KEVLAR®

## DESCRIPTION

MeCaWear A5 with KEVLAR® is a high performance paste grade polymer coating. The two-part coating incorporates a high loading of alumina and silicon carbide within the resin and hardener system that when reacted cures to provide a surface with outstanding wear protection.

MeCaWear A5 is composed of four primary ingredients; a high performance polymer, silicon carbide particles, angular alumina particles and interlocking KEVLAR fiber.

MeCaWear A5 has been formulated to allow for versatility in many applications, with no special tools and without the need for additional heat. Plus, it is suitable for use on both new and worn parts. It can be cast into irregular shapes for use as a wear pad or wear plate. MeCaFix 100 and 120 can be used to bond the precast wear pad to the surface.

## APPLICATIONS

- Pipe Elbows
- Ash Handling Pipe
- Slurry Pumps
- Screw Conveyors
- Ceramic Tile Repair
- Chutes
- Pulverizers

## COVERAGE DATA

Theoretical coverage rate data

Kit Weight	Recommended Coating Thickness	Theoretical Coverage Rate
5.5 lb (2.5 kg)	250 mils (6.3 mm)	1.7 ft <sup>2</sup> (0.158 m <sup>2</sup> )
20.9 lb (9.5 kg)	250 mils (6.3 mm)	6.8 ft <sup>2</sup> (0.632 m <sup>2</sup> )
35.2 lb (16 kg)	250 mils (6.3 mm)	11.6 ft <sup>2</sup> (1.08 m <sup>2</sup> )

Practical Coverage = Theoretical Coverage - Waste Factor

## COATING DRY FILM THICKNESS

Minimum thickness – 125 mils (3.2 mm)  
Maximum thickness – unlimited

## PACKAGING

1 L / 0.3 gal / 2.5 kg / 5.5 lb Kit  
4 L / 1.1 gal / 9.5 kg / 20.9 lb Kit  
6.8 L / 1.8 gal / 16 kg / 35.2 lb. Kit

## TECHNICAL DATA

Performance / Property		Results
Hardness	ASTM D2240	[Shore D] 82
Pull Off Adhesion	ASTM D4541	≥2,500 psi (≥17 MPa)
Impact	ASTM D2794	>125 in•lb (>1.44 kg•m)

## PHYSICAL DATA

Color	Gray
Mix Ratio	3.81:1 by volume
Mix Ratio	4:1 by weight
Sag Resistance (250 mils / 6.3 mm)	No Sag
Working Life (200g) (77°F / 25°C)	30 minutes
Low Temperature Application	>50°F (>10°C)
Percent Solids	100%
Odor	Slight to nil
Mixed Viscosity	>500,000 mPa•s (cP)
Mixed Density	2.35 g/ml
Max. Operating Temp. - Wet Service	122°F (50°C)
Max. Operating Temp. - Dry Service	195°F (90°C)
Cure Time - Touch (77°F / 25°C)	1.5 hours
Cure Time - Handle (77°F / 25°C)	5 hours

*Before applying this product, please refer to the Application Instructions.*

## YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



EUTECTIC CORPORATION  
N94 W14355 Garwin Mace Drive  
Menomonee Falls, WI 53051 USA  
Tel.: +1 (800) 558-8524

EUTECTIC CANADA  
428, rue Aimé-Vincent  
Vaudreuil-Dorion, Québec  
J7V 5V5 Canada  
Tel.: +1 (800) 361-9439



[mecatecpolymers.com](http://mecatecpolymers.com)