

Casto<u>lin Eu</u>tectic® Eutectic Castolin

MeCaWear A5FS

TECHNICAL DATA SHEET

MeCaTeC

Fast Setting Wear Compound

DESCRIPTION

MeCaTec MeCaWear A5FS, with KEVLAR®, is a fast setting, high performance paste grade polymer coating. It works in half the time when compared to our MeCaWear A5 product. This fast setting wear compound in engineered to rebuild, repair and restore equipment in minutes, reducing process downtime. MeCaWear A5FS is designed for cold weather applications and will cure down to 35°F (2°C). The twopart coating incorporates a high loading of alumina and silicon carbide within the resin and hardener system that when reacted, cures to provide a surface with outstanding wear protection. The addition of KEVLAR aids to further strengthen the polymer matrix to reduce deformation and increase the physical properties of the ceramic coating. This non sag formula allows for a single coat applications.

APPLICATIONS

•Pipe Elbows	•Ash Handling Pipe	•Slurry Pumps
 Screw Conveyors 	 Ceramic Tile Repair 	 Chutes
•Pulverizers		

COVERAGE DATA

Theoretcial coverage rate data

Kit Weight	Recommended Coating Thickness	Theoretical Coverage Rate
5.5 lb (2.5kg)	250 mils (6.3 mm)	1.8 ft² (0.167 m²)

Practical Coverage = Theoretical Coverage - Waste Factor

COATING DRY FILM THICKNESS

Minimum thickness – 125 mils (3 mm) Maximum thickness – unlimited

PACKAGING

8 L / 2.08 gal / 20 kg / 44 lb (Bulk package 8 x 2.5 kg)

TECHNICAL DATA

Performance / Property		Results
Hardness	ASTM D2240	[Shore D] 82
Pull Off Adhesion	ASTM D4541	≥ 2,500 psi (≥ 17MPa)
Impact	ASTM D2794	225 in•lb (40 kg•cm)

PHYSICAL DATA

Color	Blue-Gray
Mix Ratio	3.8:1 by volume
Mix Ratio	4:1 by weight
Sag Resistance (250 mils/6.3mm)	No Sag
Working Life (200g) (77°F / 25°C)	15 minutes
Low Temperature Application	>35°F (>2°C)
Solvent Content	Zero
Odor	Slight to nil
Mixed Viscosity	>500,000 mPa•s (cP)
Mixed Density	2.35 g/ml
Max. Operating Temp Wet Service	122°F (50°C)
Max. Operating Temp Dry Service	195°F (90°C)
Cure Time - Touch (77°F / 25°C)	30 minutes
Cure Time - Handle (77°F / 25°C)	1 hour

Before applying this product, please refer to the Application Instructions.

YOUR RESOURCE FOR PROTECTION, REPAIR AND JOINING SOLUTIONS



EUTECTIC CORPORATION N94 W14355 Garwin Mace Drive Menomonee Falls, WI 53051 USA Tel.: +1 (800) 558-8524 EUTECTIC CANADA 428, rue Aimé-Vincent Vaudreuil-Dorion, Québec J7V 5V5 Canada Tel.: +1 (800) 361-9439



mecatecpolymers.com

Statement of Liability: Due to variations inherent in specific applications, the technical information contained herein, including any information as to suggested product applications or results, is presented without representation or warranty, expressed or implied. Without limitation, there are no warranties of merchantability or of fitness for a particular purpose. Each process and application must be fully evaluated by the user in all respects, including suitability, compliance with applicable law and non-infringement of the rights of others, and Eutectic Corporation and its affiliates shall have no liability in respect thereof.