



Gas Atomized  
HVOF Thermal Spray Powder

# **TeroJet**

## **55116**



- Gas atomized 316L stainless steel powder
- Provides protection against fretting, cavitation and erosion
- Good for dimensional repair and build-up
- Applicable for some non-HVOF spray systems

# TeroJet 55116

TeroJet 55116 is a gas atomized Type 316L stainless steel powder designed specifically for application via thermal spraying. Optimum coating results will be achieved using HVOF. However, 55116 powder may also be applied using high energy, low velocity combustion or plasma NTA systems.

Each lot of powder is subjected to extensive quality checks to insure a consistent particle size distribution and chemical composition. The powder is essentially spherical in shape. The HVOF coatings produced are suitable for a wide range of applications requiring resistance to corrosion, cavitation and erosion.

## TECHNICAL DATA

Typical Values	
Microhardness:	375 DPH 300g
Hardness / R15N:	73 (HRC 27 converted)
Bond Strength:	>5,000 psi (ASTM C633)
Porosity:	< 3 %
Coating Density:	7.6 g/cc
Service Temperature:	1000° F / 538° C (Max)
As-Sprayed Roughness:	200 micro-inches AA
As-Ground Roughness:	< 40 micro-inches AA
As-Ground and Lapped:	< 10 micro-inches AA
Hall Flow:	20-25 seconds / 50g

### Powder Properties:

Nickel, Chromium, Molybdenum, Carbon, Iron

## PROCEDURE FOR USE:

### Finishing Procedure

Coatings of TeroJet 55116 may be finished by machining using carbide tools. Use flood coolant and do not overheat the coating. A finer finish is possible by rough machining using carbide tools followed by grinding. Follow the tool manufacturer's recommendations for speeds and feeds.

## TYPICAL APPLICATIONS

- Pump Impellers and Plungers
- Seal Rings
- Cylinder Liners
- Dimensional Restoration
- Turbine Buckets and Nozzle

When applying 55116 powder via the HVOF process, respiratory, hearing and eye protection is required. For general guidelines consult AWS Publication C2.1-73 and AWS T5S-85, "Recommended Safe Practices for Thermal Spraying and AWS T5S-85, "Thermal Spraying, Practice, Theory and Application." Thermal spraying is a completely safe process when performed in accordance with proper safety measures. Become familiar with local safety regulations before starting spray operations. DO NOT operate your spraying equipment or use the spray material supplied, before you have thoroughly read the equipment instruction manual. Refer to the Eutectic web site for Material Safety Data Sheet (MSDS) information. DISREGARDING THESE INSTRUCTIONS MAY BE HAZARDOUS TO YOUR HEALTH.



**Eutectic Corporation:**  
N94 W14355 Garwin Mace Dr.  
Menomonee Falls WI, 53051 USA  
+1 800. 558. 8524 • eutectic.com

**Eutectic Canada:**  
428, rue Aimé-Vincent Vaudreuil-Dorion,  
Québec J7V 5V5 Canada  
+1 800. 361. 9439 • eutectic.ca



Follow Us On...

