



Versatile Rod for Maintenance &  
Production Welding of Wrought and  
Cast Aluminum Alloys

# **TigTectic® 23**



- Excellent for high-strength, Mg bearing grades of aluminum
- Good color match, even after anodization
- Well suited for structural fabrication of pipe, tubing, sheet or extruded shapes

# TigTectic® 23

TigTectic 23 is a perfect choice for gas tungsten-arc welding of aluminum. It provides for a cosmetically clean and oxide-free weld deposit. No post-welding clean up is necessary. Alloys can be used in all-positions depending on the skill of the welder.

TigTectic 23 is recommended when welding the high strength aluminum-magnesium grades (5xxx group). Also suitable for grade 6061.

## TECHNICAL DATA

### Typical Values

<b>Tensile Strength:</b>	35,000 psi (240 N/mm <sup>2</sup> )
<b>Yield Strength:</b>	29,000 psi (200 N/mm <sup>2</sup> )
<b>Hardness:</b>	75 BHN
<b>Electrical Conductivity:</b>	IACS 41
<b>Shielding Gas:</b>	100% Argon
<b>Color Match Properties:</b>	Good*
<b>Current &amp; Polarity:</b>	AC with imposed high frequency

\*Note: TigTectic 23 will darken slightly after anodizing.

### SUGGESTED WELDING PARAMETERS:

Diameter	Welding Current			Tungsten Diameter	Filler Rod Diameter	Cup Size	Flow Rate
	Flat	Vertical	Overhead				
Up to 1/16"	60 - 90	60 - 90	60 - 90	1/16"	1/16"	1/4", 5/16", 3/8"	15 scfh
1/16" to 1/8"	125 - 160	115 - 135	120 - 160	3/32"	3/32"	3/8", 7/16"	17 scfh
1/8" to 3/16"	190 - 240	190 - 220	180 - 210	1/8"	1/8"	7/16", 1/2"	21 scfh
3/16" and up	260 - 340	220 - 260	210 - 250	3/16"	1/8"	1/2", 5/8", 3/4"	25 scfh

Note: Welding parameters for the Gas-Tungsten Arc process are based on the dimensions of the work. Optimization by trial is recommended.

## PROCEDURE FOR USE

**PREPARATION:** Base metal should be free of grease, oil oxides or other contaminants. Thin sections can be welded after suitable cleaning and surface oxide removal. Square-butt welding is acceptable for thin-gauge material. Thicker sections should be beveled to give a minimum included angle of 60°. The selection of the preferred tungsten diameter will depend on the material thickness and corresponding amperage range. This applies similarly to gas cup size.

Note: Make sure to round the tip of the filler metal rod for better heat transfer and to minimize tungsten erosion. Heavy sections should be preheated within the range of 500° to 800°F (260-426°C) for non-heat treated alloys.

**TECHNIQUE:** Adjust argon shielding gas flow. Complex, or large parts, should be supported by tack-welds and jigs. Adjust stand-off distance so that the molten pool is always protected by the shielding gas and allow the rod-end to solidify before removing it from the gas envelope.

**POST WELDING:** Slow cool after welding.

## TYPICAL APPLICATIONS

TigTectic 23 is used for fabrications involving 5xxx series alloys where good strength and improved anodized color match are required.



**Eutectic Corporation:**  
N94 W14355 Garwin Mace Dr.  
Menomonee Falls WI, 53051 USA  
+1 800. 558. 8524 • eutectic.com

**Eutectic Canada:**  
428, rue Aimé-Vincent Vaudreuil-Dorion,  
Québec J7V 5V5 Canada  
+1 800. 361. 9439 • eutectic.ca



Follow Us On...

